

# ***PLASTOIL***

## ***CHLORINATED PARAFFIN***

<b>SPECIFICATION</b>	<b>REF.TEST METHOD</b>	<b>1040</b>	<b>1045</b>	<b>152</b>
<b>COLOR , APHA</b>	ASTM D1209-69	200 (MAX)	120 (MAX)	120 (MAX)
<b>CHLORINE CONTENT</b> by WT%	ASTM E442	40 - 42	44 - 46	50 - 53
<b>SPECIFIC GRAVITY , 25°C</b>	ASTM D287	1.13 - 1.18	1.14 - 1.19	1.23 - 1.28
<b>VISCOSITY , 25°C (POISE)</b>	JIS K2283	20 - 35	2 - 3	11-20
<b>THERMAL STABILITY</b> %HCL 4HRS 175°C	JQD METHOD	0.2 (MAX)	0.2 (MAX)	0.2 (MAX)

TAIWAN, R.O.C.