

GREENFLEX ®

EVA

ML 50

Ethylene vinyl acetate copolymer

Greenflex ML 50 is an ethylene vinyl acetate copolymer (EVA) for injection moulding, compounding and extrusion.

Main Application

Greenflex ML 50 is recommended for the production of foamed and crosslinked sheets for shoes, dolls, shock absorbers and gasket.

Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	2.5	g/10min	ISO 1133
Vinyl acetate content	19	%	Internal method
Density	0.941	g/cm3	ISO 1183
Melting Point	83	°C	Internal method
Brittleness temperature	<- 80	°C	ASTM D 746
Vicat softening point (1 kg)	58	°C	ISO 306/A

Mechanical Properties *	Value	Unit	Test Method
Tensile stress at yield	4.5	MPa	ISO 527
Tensile stress at break	_	MPa	ISO 527
Elongation at break	-	%	ISO 527
Flexural modulus	40	MPa	ISO 178
Hardness Shore A	89	-	ISO 868 A
Hardness Shore D	36		ISO 868 A

(*) Values are referred to injection moulded specimens. Actual properties are typical and may vary depending upon operating conditions.



Greenflex ® is a registered trademark

This document is constituted of 2 pages

Pag 1/2

April 2017



Processing notes

Greenflex ML 50 is readily processable by the latest injection moulding equipments with excellent results. Moulding Conditions (*)

Operation temperature (°C) 140 – 200

Mould temperature (°C) 10 – 30


Storage and Handling

data.

Greenflex ML 50 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.



Pag 2/2

April 2017